



Manufactured for and Distributed
Exclusively by Sherwin-Williams

METAL REPAIR PRODUCTS

Product Comparison & Specifications

| RR&C PRODUCT | BELZONA PRODUCT | THORTEX PRODUCT | ABRASION ASTM D4060 CS17 Wheel 1000 Cycles 1 kg Load Weight Loss | ADHESION ASTM D4541 | ROCKWELL HARDNESS ASTM D2240 | COMPRESSIVE ASTM D695 | FLEXURAL ASTM D790 | TENSILE SHEAR ADHESION ASTM D1002 |
|---------------------------------------|-----------------------|----------------------|--|------------------------|------------------------------------|--------------------------|-----------------------|---|
| Ceramic Carbide Metal Repair | 1812 Ceramic | Cerami Tech HG | 25 mg | >2,500 psi | >80 | >17,000 psi | >13,000 psi | >3,500 psi |
| Ceramic Repair Paste | 1121 | Metal Tech XG | 40 mg | >2,500 psi | >80 | >16,000 psi | >13,000 psi | >3,500 psi |
| Ceramic Repair Paste High Temp | 1311 Ceramic R Metal | Cerami Tech EG | 35 mg | >2,500 psi | >80 | >15,500 psi | >13,000 psi | >3,500 psi |
| Concrete Epoxy Primer | No Equivalent | Floor-Tech SP Primer | 89 mg | >2,500 psi | 75 | 11,800 psi | >11,000 psi | >2,000 psi |
| Fluid Flow Liquid Epoxy | 1341 Supermetal Glide | Cerami Tech CR | 42 mg | >3,000 psi | >80 | >16,000 psi | >13,000 psi | >3,500 psi |
| Liquid Ceramic Epoxy | 1321 Ceramic S Metal | Cerami Tech FG | 23 mg | >2,500 psi | >80 | >15,500 psi | >13,000 psi | >3,000 psi |
| Liquid Ceramic Epoxy Elevated Temp | 1391 Ceramic | Cerami Tech HTX | 35 mg | >3,000 psi | >80 | >15,500 psi | >13,000 psi | >3,000 psi |
| Liquid Ceramic Epoxy High Temp | 1392 | No Equivalent | 37 mg | >3,000 psi | >80 | >15,500 psi | >13,000 psi | >3,500 psi |
| Machinable Multi-Purpose Repair Paste | 1111 Super Metal | Metal Tech EG | 45 mg | >2,500 psi | >80 | >17,500 psi | >13,000 psi | >13,000 psi |
| Metal Repair Paste Fast Cure | 1211/ 1221 | Metal Tech RG | 35 mg | >2,500 psi | >80 | >15,500 psi | >13,000 psi | >3,000 psi |
| Surface Tolerant Primer | No Equivalent | Corro-Tech GP | 56 mg | >2,500 psi | 70 | >12,000 psi | >11,000 psi | >2,000 psi |

ASPHALTIC EMULSION PRODUCTS

Competitor Comparison

| RR&C Product | Competitive Product |
|--------------------------------------|--|
| Corrosion Control | TECTYL 351S |
| Dampproofing | Henry 789 |
| Frame Paint Low Viscosity | Henkel AQUENCE KL or TECTYL Frame Paint XP |
| Low Viscosity Corrosion Control | Royal PC |
| Marine Void Coating | Royal Coatings Void Kote |
| Pipe Coating | PCT MC4 or MPFC-S1.0 |
| Under Body Coating | TECTYL 6427 or 6430 |
| Waterproof Membrane Brush/Roll Grade | Wetsuit 1-Part |
| Waterproof Membrane Spray Grade | Wetsuit 2-Part |

CONCRETE REPAIR PRODUCTS

Competitor Comparison

| RR&C Product | Competitive Product |
|------------------------------|---|
| Elastomeric Liquid | PolySpec Thikol FEC 2234 or Ceilcote Ceiline Series |
| Light Weight Concrete Repair | EucoRepair V100 |