

SELECTION & SPECIFICATION DATA

Type	Epoxy Paste/Caulk
Description	RR&C C/R Repair Paste/Caulk SG is a two-component 100% solids trowel applied epoxy novolac caulk formulated for use in warm conditions. This summer grade formula provides longer pot life in higher temperatures. It is commonly used to repair tank chimes or feather lap welds prior to applying Novocoat chemical resistant topcoats. It has excellent resistance to a wide range of petrochemicals, fuels, organic and inorganic acids, and alkalis.
Features	<ul style="list-style-type: none"> • 100% solids, no VOCs • Longer pot life in warm conditions • Multipurpose, durable repair composite • No shrinkage, expansion, or distortion • Quick return-to-service under suitable conditions • Fully machinable using conventional tools
Uses	<ul style="list-style-type: none"> • Fill pitted metal surfaces • Repair leaks • Rebuild pumps • Bond metal parts
Color	Light Gray
Finish	Matte
Solids Content	100% solids by volume

SUBSTRATES & SURFACE PREPARATION

All	Substrate must be clean, dry and free of contaminants.
Steel	<p>Immersion: SSPC-SP 10/NACE 2 Near White Metal Blast with angular profile of 2.5 - 3.5 mils.</p> <p>Non-immersion: SSPC-SP 6/NACE 3 Commercial Blast with angular profile of 1.5 - 3.0 mils, SSPC-SP 2 Hand Tool or SSPC-SP 3 Power Tool Cleaning are suitable for mild environments.</p> <p>Self-priming on steel.</p>
Weld Repair	Use a flame to sweat out oil from deeply impregnated surfaces. Stabilize cracks by drilling the extremities. Long cracks should be drilled, tapped, and bolted every few inches. Vee-out all cracks using a file. Degrease using clean rags.

MIXING & THINNING

Ratio	1A:1B by volume
Mixing	Mix equal parts of the resin and hardener thoroughly until color of material is uniform and free of streaks.
Thinning	Do not thin.
Pot Life	<p>25 minutes in a 150g mass at 86°F (30°C)</p> <p>16 minutes in a 150g mass 122°F (50°C)</p> <p>Pot life is shorter at higher temperatures. A larger volume of mixed material will have a shorter pot life than a smaller volume.</p>
Cleanup	MEK or Acetone

APPLICATION GUIDELINES

Conditions	Substrate surface temperature 70°F - 140°F (21°C - 60°C) and at least 5°F (3°C) above the dew point and rising. If surface temperature is above 140°F (60°C), consult Sherwin-Williams for guidance.
Application	Apply directly onto the prepared surface with the spreader or mixing knife provided. Press down firmly to remove entrapped air, fill all cracks, and ensure maximum contact with the surface. Use reinforcement cloth over holes and cracks.
Brush & Roller	Brush or roller can be used to smooth uncured surface with solvent if desired.

CURE SCHEDULE & RECOAT WINDOW

TEMPERATURE	MINIMUM RECOAT	MAXIMUM RECOAT	RETURN-TO-SERVICE (HYDROCARBON IMMERSION)
86°F (30°C)	1 hour	48 hours	7 days
104°F (40°C)	1 hour	24 hours	48 hours
122°F (50°C)	30 minutes	8 hours	24 hours
Return-to-service will vary with chemical exposure. Consult with Sherwin-Williams for guidance.			
Tack free at 86°F (30°C) ASTM D1640			65 minutes for 125 mil DFT film
Tack free at 122°F (50°C) ASTM D1640			23 minutes for 125 mil DFT film
Dry hard at 86°F (30°C) ASTM D1640			180 minutes for 125 mil DFT film
Dry hard at 122°F (50°C) ASTM D1640			30 minutes for 125 mil DFT film

RR&C C/R Repair Paste/Caulk SG

PACKAGING, ESTIMATING & HANDLING

ITEM#	PRODUCT	PACKAGING
CERPESG-2GLKT-SW	RR&C C/R Repair Paste/Caulk SG	24 lb (10.88 kg) Kit
	Paste/Caulk Kit, Light Gray	
	- Part A Resin, White	12.4 lb (5.62 kg) Pail
	- Part B Hardener, Black	11.6 lb (5.26 kg) Pail

Theoretical Coverage

53.3 square feet per 2-gallon kit at 60 mils.
25.6 square feet per 2-gallon kit at 125 mils.

Coverage will vary depending on application. Allow for loss in mixing and application.

Storage & Shelf Life

Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 24 months for part A and 12 months for part B when stored in a dry area at 75°F (24°C). Actual shelf life may vary with storage conditions. Do not store below 40°F (4°C) or above 110°F (43°C).

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with Sherwin-Williams.

SAFETY

Safety

Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.

Ventilation

Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	VALUE
Pull-off adhesion, dry ASTM D4541 Blasted steel 1 coat	>2,850 psi (20 MPa)
Flash Point	Greater than 250°F (121°C)
Specific gravity	Part A: 0.53 Part B: 1.40
VOC	0 lb/gal (0 g/L)
Density	Part A: 12.7 lbs/gal (1.5 kg/L) Part B: 11.7 lbs/gal (1.4 kg/L) Mixed: 12.2 lbs/gal (1.5 kg/L)

SERVICE TEMPERATURE

SERVICE	MAXIMUM TEMPERATURE
Dry	350°F (176°C)
Splash/spill	293°F (145°C)
Immersion	194°F (90°C)

Temperature limitations will vary with chemical exposure. Consult Sherwin-Williams for guidance.

Rev. 12/2025



Manufactured for and Distributed
Exclusively by Sherwin-Williams