

# RR&C Cold Applied Bituminous Adhesive

## SELECTION & SPECIFICATION DATA

<b>Type</b>	Cold Adhesive
<b>Description</b>	RR&C Cold Applied Bituminous Adhesive is a single-component, asbestos-free, asphaltic commercial roofing adhesive designed to adhere modified bituminous membranes. It can be sprayed or applied using a squeegee. RR&C Applied Bituminous Adhesive is comprised of a special, low-odor formula that leads the bituminous roofing industry in adhesion.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Single-component</li> <li>• Low odor</li> <li>• Cold-applied</li> <li>• Elastomeric</li> </ul>
<b>Uses</b>	Adhesive for single- and multi-ply SBS and select APP roofing membranes.
<b>Color</b>	Black
<b>Primer</b>	Self-priming
<b>Solids Content</b>	86% by weight
<b>VOC Value(s)</b>	<250 g/L (2.09 lbs/gal)
<b>Limitations</b>	Not all APP membranes are alike, and adhesion to these modified membranes should be tested. Do not use with membranes containing a burn-off film.

## SUBSTRATES & SURFACE PREPARATION

<b>All</b>	All surfaces must be clean and free from debris and loose scale material or anything that may interfere with adhesion or act as a bond breaker with the desired substrate.
------------	--

## MIXING & THINNING

<b>Mixing</b>	No mixing necessary
<b>Thinning</b>	Do not thin
<b>Cleanup</b>	Mineral spirits or similar solvent

## APPLICATION GUIDANCE

<b>Airless Spray</b>	Pump size: 45:1 or greater Spray hose: 200 ft x 3/4-inch ID Whip length: 15 ft x 1/2-inch ID
<b>Squeegee</b>	1/4-inch serrated squeegee

## PACKAGING, ESTIMATING & HANDLING

ITEM#	PACKAGING
CAA-005-SW	Pail - 4.7 gallons
CAA-053-SW	Drum - 53 gallons

<b>Theoretical Coverage Rate</b>	1.5 - 2 gallons per square, depending on substrate.
----------------------------------	---

<b>Storage &amp; Shelf Life</b>	Estimated shelf life is 12 months when stored in a dry area at 75°F (24°C). When kept at recommended storage conditions and in original unopened containers. Actual shelf life may vary with storage conditions. Do not store below 40°F (4°C) or above 110°F (43°C). Store indoors. Always inspect the product prior to use.
---------------------------------	---

## SAFETY

<b>Safety</b>	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
---------------	--

<b>Ventilation</b>	Use in well ventilated areas.
--------------------	-------------------------------

## TYPICAL PHYSICAL PROPERTIES

Lap shear testing after 24 hours has shown that RR&C Cold Applied Bituminous Adhesive meets or exceeds the performance attributes of ASTM D3019.

Rev. 12/2025



Manufactured for and Distributed  
Exclusively by Sherwin-Williams