

# RR&C Elastomeric Membrane - Trowel Grade

## SELECTION & SPECIFICATION DATA

<b>Type</b>	Asphalt Modified Polyurethane
<b>Description</b>	RR&C Elastomeric Membrane - Trowel Grade is a very flexible, cold-applied liquid waterproofing. This trowel-grade material can be used alone or as a detail mastic in conjunction with RR&C Elastomeric Membrane - Self Level.
<b>Features</b>	<ul style="list-style-type: none"> <li>• Crack bridging</li> <li>• Seamless monolithic</li> <li>• Flexible elastomer</li> <li>• High elongation</li> <li>• Cold-applied</li> <li>• High film build</li> <li>• Sag resistant</li> </ul>
<b>Uses</b>	<ul style="list-style-type: none"> <li>• Foundation waterproofing</li> <li>• Vertical waterproofing</li> <li>• Between-slab (split-slab) waterproofing</li> <li>• Below-grade waterproofing</li> <li>• Secondary containment</li> <li>• Wastewater containment</li> <li>• Crack isolation</li> </ul>
<b>Color</b>	Black
<b>Primer</b>	Self-priming on most concrete and metal surfaces. RR&C Concrete Epoxy Primer may be used to reduce the risk of outgas blisters on concrete.
<b>Topcoat</b>	Aggregate broadcast or coatings
<b>Film Thickness (FT)</b>	125 mils per coat
<b>Limitations</b>	Will lose gloss, discolor, and chalk in sunlight
<b>Cure Schedule</b>	30 minutes at 90°F (32°C) 40 minutes at 75°F (24°C) 50 minutes at 60°F (16°C)

## SUBSTRATES & SURFACE PREPARATION

<b>All</b>	Substrate must be clean, dry and free of contaminants.
<b>Steel</b>	<p>Immersion: SSPC-SP10 Near White Metal Blast with angular profile of 2.5 - 3.5 mils.</p> <p>Non-immersion: SSPC-SP6 Commercial Blast with angular profile of 1.5 - 3.0 mils, SSPC-SP2 Hand Tool or SSPC-SP3 Power Tool Cleaning are suitable for mild environments.</p> <p>Self-priming on steel.</p>

### **Concrete and Concrete Masonry Unit (CMU)**

Concrete must be cured 28 days at 75°F (24°C) and 50% relative humidity or equivalent. Prepare surfaces in accordance with ASTM D4258 Surface Cleaning of Concrete and ASTM D4259 Abrading Concrete. Voids in concrete surfaces may require filling. Mortar joints should be cured a minimum of 15 days. Prime with RR&C Concrete Epoxy Primer.

### **Previously Painted Surfaces**

Consult with your Sherwin-Williams representative.

## MIXING & THINNING

### **Mixing**

Do not mix by hand. Always inspect the product prior to use to make sure it is smooth and homogeneous. Use an electric or air driven 1/2-inch drill with an 8-inch square metal mixing blade. Premix Part A for 1 minute to reduce viscosity, taking care not to draw air into the mix. Add Part B hardener slowly over a period of at least 45 seconds. Move the mix blade in a clockwise and counter-clockwise motion for a full 3 minutes. Do not allow moisture to contaminate the mixing process. Ensure that the entire contents of the packaged Part B is mixed into the entire contents of the packaged Part A.

### **Thinning**

Do not thin

### **Ratio**

45A:1B by weight

### **Pot Life**

30 minutes at 90°F (32°C)  
 40 minutes at 75°F (24°C)  
 50 minutes at 60°F (16°C)  
 Not recommended below 60°F (16°C)

Pot life is shorter at higher temperatures. A larger volume of mixed material will have a shorter pot life than a smaller volume.

### **Recoat Window**

Recoat window is typically 1 - 4 hours at 77°F (25°C). Cured material over 4 hours may need to be prepared as stated in the repair and maintenance section below.

### **Cleanup**

Cured material cannot be recovered. Flush and clean all equipment after use with mineral spirits or equivalent solvent. Cured material can be soaked in solvent to aid in clean-up.

## APPLICATION GUIDELINES

### **Trowel Application**

Typically applied by gloved hand or trowel.

### **Tie-in**

Edges of the old compound should be roughed up with a wire bristle brush to expose a fresh surface. That surface should then be wiped with an aromatic or mineral spirit solvent and allowed to dry. Subsequent material can be applied over the prepared area.

# RR&C Elastomeric Membrane - Trowel Grade

## PACKAGING & HANDLING

ITEM#	PACKAGING
HPEMTG-5GLB-SW	Pail - 4 gallons

### **Storage & Shelf Life**

Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 2 years when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.

If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with your Sherwin-Williams representative.

## SAFETY

### **Safety**

Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.

### **Ventilation**

Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

## TYPICAL PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUE
Color	Black
Density	8.6 lb/gallon (1,030 kg/m <sup>3</sup> )
Elongation, ASTM D412	>200%
Tensile strength, ASTM D412	>100 psi (0.7 MPa)
Bond to carbon steel, ASTM D412	>100 psi (0.7 MPa)
Permeance, ASTM C96, method E, wet method	<0.1 perms
Mix ratio	46:1 by weight
Service temperature range	-40°F (-40°C) to 170°F (77°C)
- if directly exposed	-40°F (-40°C) to 200°F (93°C)
- behind masonry/concrete	

Rev. 12/2025



Manufactured for and Distributed  
Exclusively by Sherwin-Williams