

RR&C Liquid Ceramic Epoxy Elevated Temp

SELECTION & SPECIFICATION DATA

Type	Novolac Epoxy
Description	RR&C Liquid Ceramic Epoxy Elevated Temp is a 100% solids novolac epoxy coating for floors, secondary containment, fume ducts, piping and bulk storage tanks. Densely cross-linked, it resists permeation by organic acids, caustics and petrochemicals, while ceramic fillers offer enhanced abrasion and temperature resistance.
Features	<ul style="list-style-type: none"> • Excellent resistance to wide range of acids and caustics • Low permeation rate for tank lining service • Solvent free - 100% solids • Suitable for single leg application • Quick return-to-service (24 hours at 77°F (25°C) for hydrocarbon immersion service)
Uses	<ul style="list-style-type: none"> • Floors and trenches in chemical process areas • Secondary containment areas • Process equipment supports and pads • Heat exchangers and tube sheets • Internal pipeline and vessel linings
Color	Light gray, red
Finish	Gloss
Dry Film Thickness (DFT)	2 - 3 coats at 10 - 12 mils each 3 - 4 coats at 10 - 12 mils each for high temperatures/severe chemical service
Solids Content	99 - 100% by volume

SUBSTRATES & SURFACE PREPARATION

All	Substrate must be clean, dry and free of contaminants.
Steel	<p>Immersion: SSPC-SP10 Near White Metal Blast with angular profile of 2.5 - 3.5 mils.</p> <p>Non-immersion: SSPC-SP6 Commercial Blast with angular profile of 1.5 - 3.0 mils, SSPC-SP 2 Hand Tool or SSPC-SP 3 Power Tool Cleaning are suitable for mild environments.</p> <p>Self-priming on steel.</p>
Concrete or Concrete Masonry Unit (CMU)	Concrete must be cured 28 days at 75°F (24°C) and 50% relative humidity or equivalent. Prepare surfaces in accordance with ASTM D4258 Surface Cleaning of Concrete and ASTM D4259 Abrading Concrete. Voids in concrete surfaces may require filling. Mortar joints should be cured a minimum of 15 days. Prime with RR&C Concrete Epoxy Primer.
Previously Painted Surfaces	Consult with your Sherwin-Williams representative.

MIXING & THINNING

Ratio	3A:1B by volume
Mixing	Power mix separately, then combine and power mix. Do not mix partial kits.
Thinning	Brush: Up to 12.8 oz/gal (10%) with Sherwin-Williams 54 reducer Roller: Up to 12.8 oz/gal (10%) with herwin-Williams 54 reducer
Pot Life	30 minutes at 75°F (24°C) Pot life is shorter at higher temperatures. A larger volume of mixed material will have a shorter pot life than a smaller volume.
Cleanup	MEK or Acetone

APPLICATION GUIDELINES

Brush & Roller	Multiple coats may be required to obtain desired appearance, recommended dry film thickness and adequate hiding. Avoid excessive re-brushing or re-rolling. For best results, tie-in within 10 minutes at 75°F (24°C).
Brush	Medium bristle brush.
Roller	Short-nap synthetic roller cover with phenolic core.

CURE SCHEDULE & RECOAT WINDOW

TEMPERATURE	MINIMUM RECOAT	MAXIMUM RECOAT	RETURN-TO-SERVICE (HYDROCARBON IMMERSION)
50°F (10°C)	8 hours	24 hours	7 days
77°F (25°C)	3 hours	12 hours	24 hours
140°F (60°C)	Not recommended		4 hours

Dry-to-touch: 4 hours at 77°F (25°C)

Return-to-service will vary with chemical exposure. Consult with your Sherwin-Williams representative for guidance.

RR&C Liquid Ceramic Epoxy Elevated Temp

PACKAGING, ESTIMATING & HANDLING

ITEM#	PRODUCT	PACKAGING
LCEET-1GLKT-SW	RR&C Liquid Ceramic Epoxy Elevated Temp	0.95 gallons
	- Part A Resin, Light Gray	88 fl oz (2.6 L)
	- Part B Hardener	28 fl oz (0.88 L)

Theoretical Coverage
 160 square feet per gallon at 10 mil
 133 square feet per gallon at 12 mils
 Allow for loss in mixing and application

Storage & Shelf Life
 Maintain products in original packaging and sealed until ready for use. Estimated shelf life is 12 months when stored in a dry area at 70°F (21°C). Actual shelf life may vary with storage conditions.
 If there is any question with respect to the quality of the components, check reactivity prior to use. For assistance consult with your Sherwin-Williams representative.

SAFETY

Safety
 Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.

Ventilation
 Provide thorough air circulation during and after application until the material has cured when used in enclosed areas.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	SYSTEM	VALUE
Dry adhesion ASTM D4541	Blasted steel 1 coat	>3,000 psi
Wet adhesion ASTM D4541	Blasted steel 1 coat	>3,000 psi
Abrasion resistance ASTM D4060 1000 cycles, CS17 wheel, 1000 gm load	Blasted steel 1 coat	65 mg loss 0.5 mil loss
Compressive strength ASTM C109		10,000 - 13,000 psi
Hardness ASTM D2240	Blasted steel 1 coat	84 Shore D

TEMPERATURE RESISTANCE

SERVICE	MAXIMUM TEMPERATURE
Dry, continuous	300°F (149°C)
Dry, non-continuous	350°F (177°C)
Under insulation	300°F (149°C)

Temperature limitations will vary with chemical exposure. Consult with your Sherwin-Williams representative for guidance.

Discoloration and loss of gloss occur above 200°F (93°C) but do not affect performance.

Rev. 12/2025



Manufactured for and Distributed
 Exclusively by Sherwin-Williams