

## SELECTION & SPECIFICATION DATA

<b>Type</b>	Asphalt Cutback Primer
<b>Description</b>	RR&C Roofing Primer is a concrete prime coat for bituminous mastic type protective coatings and adhesives. After curing, its penetrative value improves the cohesion between weakly bonded particles and provides a firm surface to which heavier compounds can bond. It is an excellent black coating with good hiding power and is recommended for covering weathered vapor seals to rehabilitate and restore their appearance and as a general-purpose asphalt coating or primer.
<b>Uses</b>	<ul style="list-style-type: none"> <li>• Prime coat for porous and rough surfaces</li> <li>• Asphalt base coating</li> <li>• Vapor and moisture barrier coating</li> </ul>
<b>Color</b>	Black
<b>Topcoats</b>	Consult your Sherwin-Williams representative
<b>Finish</b>	Black
<b>Dry Film Thickness</b>	5 - 15 mils
<b>Solids Content</b>	50% ± 5% by weight
<b>VOC Value(s)</b>	>450 g/L (3.76 lbs/gal)

## SUBSTRATES & SURFACE PREPARATION

<b>All</b>	All surfaces must be clean and free from debris and loose scale material or anything that may interfere with adhesion or act as a bond breaker with the desired substrate.
------------	--

## MIXING & THINNING

<b>Mixing</b>	No mixing necessary
<b>Thinning</b>	Do not thin
<b>Cleanup</b>	Mineral spirits or equivalent solvent

## APPLICATION GUIDANCE

<b>Spray Application</b>	Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.
<b>Airless Spray Single Leg</b>	Pump size: 15:1 or greater Hose length: 200 ft x 1/2-inch ID Whip length: 15 ft x 1/4-inch ID
<b>Brush</b>	Apply with a wide fiber brush in order to create a smooth uniform film.
<b>Roller</b>	Use a low nap phenolic core roller.

## PACKAGING, ESTIMATING & HANDLING

ITEM#	PACKAGING
SRP-005-SW	Pail - 4.7 gallons
SRP-053-SW	Drum - 53 gallons
<b>Theoretical Coverage Rate</b>	160 square feet per gallon at 10 wet mils.
<b>Storage &amp; Shelf Life</b>	Estimated shelf life is 12 months when stored in a dry area at 75°F (24°C). Actual shelf life may vary with storage conditions. Do not store below 40°F (4°C) or above 110°F (43°C). Store indoors. This product is not affected by excursions below published storage temperatures. Always inspect the product prior to use to make sure it is smooth and homogeneous.

## SAFETY

<b>Safety</b>	Mixes and applications of this product present a number of hazards. Read and follow the hazard information, precautions and first aid directions on the individual product labels and safety data sheets before using.
<b>Ventilation</b>	Thorough air circulation must be used during and after application until the product is cured. User should test and monitor exposure levels to ensure all personnel are within safe limits. Consult product SDS for further information.

## TYPICAL PHYSICAL PROPERTIES

SPECIFICATIONS	CATEGORY	RESULTS
ASTM D41	-	Pass

Rev. 12/2025



Manufactured for and Distributed  
Exclusively by Sherwin-Williams